


# SAREMCO Dental restorative system with apt

# 1



cmf etch  
(optional)



etch



rinse  
thoroughly




dry  
with oilfree  
air, keep dry

etch


# 2




apt unibond



apply  
and massage



dry  
with oilfree,  
air, keep dry



cure

bond

Exposure time

|               |                                  |                                    |
|---------------|----------------------------------|------------------------------------|
| light power   | $\geq 500$<br>mW/cm <sup>2</sup> | $\geq 1'200$<br>mW/cm <sup>2</sup> |
| exposure time | 20 sec.                          | 10 sec.                            |

*Note: apt unibond is a self-etching-adhesive and is applicable with all common etch techniques (non-etch, selective etch, total etch, etc.).*

# 3

## restore




apt flow



apt composite



line and cure  
(apt flow  
optional)



restore and  
cure  
layer by layer



restore and  
cure  
(small cavities)  
apt flow

Exposure time for increments of 2mm

|                 |                          |                          |
|-----------------|--------------------------|--------------------------|
| light power     | ≥ 500 mW/cm <sup>2</sup> | ≥ 800 mW/cm <sup>2</sup> |
| apt all colours | 40 sec.                  | 20 sec.                  |